

Standard	Test Method	Result
EN 1936:2006	Bulk Density	2700 kg/m ³
EN 1926:2006	Compressive Strength	184 MPa
EN 12371:2010	Compressive Strength After 48 Cycles, Freeze-Thaw	174 MPa
EN 12372:2006	Flexural Strength	15.7 MPa
EN 12371:2010	Flexural Strength After 12 Cycles, Freeze-Thaw	16.8 MPa
EN 12371:2010	Flexural Strength After 48 Cycles, Freeze-Thaw	15.7 MPa
EN 13755:2008	Water absorption	0.08%
EN 1936:2006	Porosity	0.24%
EN 14157:2004 EN 1341: 2012 EN 1342:2012	Abrasion resistance (sawn)	26.8 mm
EN 14231 :2003 EN 1341 :2012 EN 1342:2012	Slip Resistance (Polished)	40 SRV Dry 7 SRV Wet