

Standard	Test Method	Result
ASTM C97	Bulk Density	2,620 kg/m ³
ASTM C170	Compressive Strength	60.45 MPa
ASTM C880	Flexural Strength	9.97 MPa
ASTM C99	Modulus of Rupture	13.29 MPa
ASTM C97	Water absorption	1.49%
ASTM C241:97	Abrasion	9.86 Ha
AS/NZS4586	Slip Resistance	58
AS/NZS 4455.1	Salt Resistance	0.11%