

Standard	Test Method	Result
ASTM-C170	Compressive Strength	60.45 MPa
ASTM-C241:97	Abrasion Resistance	9.86 (Ha)
ASTM - C880	Flexural Strength	9.97 MPa
ASTM - C99	Modulus of Rupture	13.29 MPa
ASTM - C97	Bulk Specific Gravity	2.62 (gm/CM ³)
ASTM - C97	Water Absorption	1.49%