

Standard	Test Method	Result
EN 1936:2006	Bulk Density	2334 kg.m ⁻³
EN 12372:2006	Flexural Strength	9.6 MPa
EN 13755:2008	Water absorption	5.4%
EN 12371:2010	Frost Resistance	8.6 MPa
EN 1936:2006	Porosity	13.8%
EN 14157:2004	Abrasion	24.5 {mm}
EN 14231:2003	Slip Resistance	Dry 70 SRVU
		Wet 72 SRVU