

Standard	Test Method	Result
ASTM C97-02	Bulk Density	2.49 g/cm ³
ASTM C170-99	Compressive Strength	62.0 MPa
BS EN 12372:1999	Flexural Strength	15.5 MPa
ASTM C97-02	Water absorption by volume	4.1%
BS EN 12371:2001	Frost Resistance (48 cycles)	15.5 MPa
ASTM C241-97	Abrasion	50.0