

Standard	Test Method	Result
EN 12440	Bulk Density	2621 kgs/m ³
EN 12440	Flexural Strength	16.2 MPa
EN 12440	Water absorption	0.5%
EN 12440	Frost Resistance (external use)	No change after 48 cycles
EN 12440	Open Porosity	1.4%
EN 12440	Abrasion	19.9 mm
EN 12440	Slip Resistance	Polished Dry & Wet 118
		Honed Dry & Wet 31