

Standard	Test Method	Result
ASTM C97	Density	2.95 T/m ³
ASTM C170	Compressive strength	108.3 Mpa
ASTM C880	Flexural Strength	15.1 Mpa
ASTM C97	Porosity	1.82%
ASTM C241	Abrasion	18.45