

| Standard | Test Method | Result |
|-------------------|----------------------|--|
| BS EN 1097-6:2000 | Bulk Density | 2.88 g/cm ³ |
| BS EN 196-1:2005 | Compressive strength | Dry 221 N/mm ² Wet 209 N/mm ² |
| BS EN 196-1:2005 | Flexural strength | 30.6 N/mm ² |
| BS EN 1097-6:2000 | Water absorption | 0.51% |
| BS EN 1097-6:2000 | Porosity | 0.69% |
| BS EN 1097-1:1996 | Abrasion | 10.2% |